

FUEL CELL ELECTRODE

CROSS REFERENCES

The present invention relates to my copending Applications 10/072,166 filed 02/11/2002 and 10/392,608 filed 03/21/2003.

BACKGROUND OF THE INVENTION

The invention is a consumable electrode for use in a fuel cell of the general character of those described in the cross-references. In these designs a cathode electrode is designed as a tape structure confining between its outer top and bottom membranes, respectively referred to as the carrier insulation and the conductor tape, the active ingredient of alkali metals, alkaline earth metals and wicking material. The present invention is a method of construction which enhances the manufacture and electrical generating capability of this type of electrode.

In the previous design of Ref. 1 a sodium dispersion in a neutral medium was applied to a lower carrier insulation tape and a conductor tape placed on top and both tapes were sealed at their contacting edges hermetically sealing the chemically reactive reagents within preventing their oxidation. In the present invention the carrier insulation tape and the conductor tape are manufactured as a single aluminized tape in which a continuous sheet of sodium metal foil is laid down and positioned on the left half of the tape and the right half of the tape is then folded over it and the two edges are hermetically sealed. In some instances the sodium sheet may be laid down upon the carrier

1 insulation in short segments and sealed at their ends to prevent blow-
2 back of hydrogen gases into the unreacted part of the tape as is shown
3 in the Cross-References.

4 Sodium has a very low melting point and is very malleable at
5 room temperature and can be cold rolled into thin foil sheets from its
6 extruded wire. Knowing the extruded wire diameter and the metal foil
7 thickness permits a more accurate accounting of sodium per inch of
8 tape width and length. Sodium is also quite reactive and is easily
9 oxidized in contact with the air and therefore must be processed in an
10 inert environment. To prevent oxidation during its formation and
11 during its processing in the electrode tape construction, a depolarizing
12 agent is applied to the sodium metal foil surface to lower its incidental
13 contact with air during electrode assembly and reduce the effect of air
14 diffusion through the aluminized carrier insulation and thereby increase
15 its useful shelf-life.
16

17 In the previous consumable electrode designs presented in the
18 Cross-References a separate means was employed for passing the
19 electrode into the electrolyte. In the present invention a bead-chain is
20 inserted between the edges of the folded tape during the sealing
21 process and sealed in place between the two edges. The bead-chain,
22 pulled by bead-gears will assist the passage of the electrode through
23 the electrolyte preventing tensile failure of the electrode tape during the
24 high exothermic reaction of the sodium foil with the water in the
25 electrolyte.
26
27
28

SUMMARY OF THE INVENTION

A consumable electrode containing a sodium foil is constructed from a single piece of aluminized tape which is folded at its center and its edges are brought together and sealed hermetically encompassing the sodium foil. In an alternate design a bead-chain is inserted in the edges of the folded aluminized tape containing the sodium foil.

It is an object of the invention to simplify the construction of a consumable electrode from a single tape.

It is another object of the invention to apply the sodium initiator of a consumable electrode as a metal foil such that its content is more evenly distributed per linear length of the tape electrode.

It is yet another object of the invention to provide a means of carrying a consumable electrode through a chemically reacting electrolyte by the addition of a bead-chain interposed between the sealing edges of the electrode such that it is fixedly sealed with the tape.

DRAWINGS OF THE INVENTION

Drawings of the invention are presented as a part of the specification.

Fig. 1 shows a length of aluminized tape holding near one edge a length of sodium foil.

Fig. 2 shows the length of aluminized tape of Fig. 1 folded at its center and its edges brought together and sealed at its edges.

1 Fig. 3 is a drawing of a beaded-chain of the general type to be
2 described.

3
4 Fig. 4 is a drawing of a bead-chain inserted and sealed between the
5 edges of the consumable electrode.
6

7 Fig. 5 is a drawing of the consumable electrode being carried through
8 the electrolyte by the bead-chain gearing.
9

10 DETAILED DESCRIPTION OF THE INVENTION

11 Sodium metal is extruded as a wire which is subsequently cold
12 rolled into continuous sheets of thin foil 1 which is passed through a
13 misting chamber covering both surfaces of foil 1 with a depolarizing
14 agent. In Fig. 1 a segment of foil 1 is positioned at one edge of an
15 aluminized polymer tape hereinafter called the carrier tape 2. Said
16 carrier tape 2 is folded along its longitudinal center-line 3 and its two
17 edges brought together at point 4 and sealed along the entire length of
18 the carrier tape 2, hermetically sealing and encasing sodium foil 1
19 within as shown in Fig. 2 forming consumable electrode 5 which is
20 subsequently rolled upon a spool.
21

22 Turning now to Fig. 3 which is a drawing of a polymer bead-
23 chain 6 comprising a column of polymer spheres 7 formed at regularly
24 spaced intervals upon its surface. Bead-chain 6 is inserted between the
25 two edges of folded aluminized tape 2 at point 4 and sealed in place
26 with both edges of polymer tape 2 forming consumable electrode 8 as
27 shown in Figure 4. Those skilled in the art will readily perceive that
28

Numbered Elements of the Drawings

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28

1. Sodium foil
2. Polymer tape
3. Centerline
4. Sealing point
5. Electrode
6. Bead-chain
7. Spheres
8. electrode
- 9.
10. Bead-gear (3 places)
11. Vat
12. Electrolyte
13. Pin roller
- 14.
- 15.
16. Guide roller